



solutions in prototyping
igw mbh

Polyurethan, Shore A 98

Material properties

Characteristic	Iso	Unit	Shore D
Hardness (23°C)	868	Shore	A 98
Tear resistance	34	N/mm	68
Tensile strength	R527	MPa	25
Heat deflection temperature	75 Ae	°C	130
Breaking elongation	R527	%	375
Density (23°C)	1183	g/cm ³	ca. 1,1

17.05.2019